

Technical Data Sheet

Ref: P216
Date: 29-06-2018
Version: 007
Page: 1 of 1

Commercial Name: FERROXIDE® 216

Manufacturer: Venator Pigments S.p.A.

General Description

Chemical Formula: Fe_2O_3
Type: Red Iron Oxide Pigment
Colour Index: Pigment Red 101 (77491)
CAS No.: 1309-37-1
EINECS No.: 215-168-2
Form: Powder

Technical Data - Specified Values

	<u>min.</u>	<u>max.</u>	<u>Test Method</u>
Colour Tolerance against current standard ⁽¹⁾ : ΔE^*		1.5	LO-11
Relative Tinting Strength (%)	95	105	LO-11
Water Soluble Salts ⁽²⁾ (%)		0.5	LO-05
Chloride Content (%)		0.1	LO-43
Sieve Residue on 44 μ Mesh (%)		0.5	LO-08
pH	6	9	LO-06

Technical Data - Typical Values

Fe_2O_3 Content (%)	97+	LO-16
Particle Shape	Spheroidal	T.E.M. ⁽³⁾
Average Particle Size (μm)	0.1	T.E.M. ⁽³⁾
Specific Gravity (g/cm^3)	approx. 5.0	ISO DIN 787/10
Tamped Apparent Density (g/cm^3)	approx. 0.7	LO-10
Water Content ex. works (%)	≤ 1	LOG-14

Standard Packaging: 25 kg bags, 1000 kg Supersacks

Notes:
(1) Grey Cement
(2) Sulphates
(3) T.E.M. = Transmission electron microscopy
All data is given in good faith but without warranty. Ferrooxide 216 complies with EN 12878 (Category B). 0840-CPD-1014-090074-08

Venator, Via G. Reiss Romoli, 44/12 - 10148 Torino, Italy
Tel: +39 011-228 05 01 Fax: +39 011-226 92 75 info@venatorcorp.com www.venatorcorp.com

Venator is a trading name of Venator Pigments S.p.A., Via G. Reiss Romoli, 44/12 10148 TORINO. Cap. Soc. €3.819.930 I.V. – C.F. e Iscr. R.I. Torino 02146370263 – P.IVA IT 07365630016. Società soggetta di direzione e coordinamento di Venator Italy S.r.l. unipersonale.